

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G01F 1/684, 1/688	A1	(11) International Publication Number: WO 98/50763 (43) International Publication Date: 12 November 1998 (12.11.98)
(21) International Application Number: PCT/GR97/00040 (22) International Filing Date: 25 November 1997 (25.11.97) (30) Priority Data: 970100176 7 May 1997 (07.05.97) GR (71) Applicant (for all designated States except US): NCSR "DEMOKRITOS" [GR/GR]; P.O. Box 60228, Aghia Paraskevi, Attikis, GR-153 10 Athens (GR). (71)(72) Applicants and Inventors: NASSIOPOULOU, Androula, G. [GR/GR]; Institute of Microelectronics, NCSR "Demokritos", P.O. Box 60228, Aghia Paraskevi, Attikis, GR-153 10 Athens (GR). KALTSAS, Grigoris [GR/GR]; NCSR "Demokritos", P.O. Box 60228, Aghia Paraskevi, Attikis, GR-153 10 Athens (GR).		(81) Designated States: CA, CN, JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: INTEGRATED GAS FLOW SENSOR BASED ON POROUS SILICON MICROMACHINING

(57) Abstract

The device of the integrated gas flow sensor is fabricated on a membrane made of a bilayer of SiO₂/polysilicon on bulk crystalline silicon. The membrane is either suspended on a deep cavity formed on bulk crystalline silicon, or it is lying on a thick oxidized porous silicon layer. The cavity under the membrane is fabricated by bulk silicon micromachining using porous silicon as a sacrificial layer. The sensing element is composed of a two series of integrated thermocouples on the left and right side of a heated resistor. The thermocouples are composed of parallel strips of aluminum/p-type polysilicon or p-type/n-type polysilicon, in contact on one end. The heated resistor is a p-type polysilicon strip. A second polysilicon resistor outside the membrane in series with the heated resistor serves to stabilize the heating power to better than 0.05 %. The fabrication process is C-MOS compatible and the sensor is easily integrated on silicon with its readout electronics.



BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Title: "Integrated gas flow sensor based on porous silicon micromachining"

5 Technical field

The device is an integrated gas flow sensor which uses a series of integrated thermocouples, the hot contact of which is on a polycrystalline silicon membrane and the cold contact on bulk silicon. The membrane is
10 either suspended on a deep cavity formed into silicon by using porous silicon as a sacrificial layer or as an alternative the porous silicon is not removed but oxidized and it is used as thermal isolation layer. A heated resistor is also integrated on the membrane. Integrated thermopiles measure gas flow through Seebeck effect. The polysilicon thermally isolated resistor
15 is heated with constant power and the temperature is measured by the thermopiles. A gas flow changes the resistor temperature and therefor the output voltage of the thermopile. We can also use the flow-dependent heat transport from the heater into the surrounding gas. The gas flow generates a temperature difference between downstream and upstream points on the
20 device, which provides different thermopile signals.

Technical level of existing technology

25 Existing integrated gas flow sensors on silicon use in general a heated resistor and the temperature difference due to the gas flow is measured by a transistor pair or a resistance bridge (examples are : The European patent No 0490764A1, the US patent No 4,680,963 and the US patent No 5,231,878).). The use of integrated thermocouples increases the
30 sensitivity of the device, which is controlled by the number of the thermocouples. Thermopiles have also various attractive properties compared with the above mentioned sensors. First, the thermopile is based on the self-generating Seebeck effect, in which the input signal supplies the power for the output signal. This ensures that the thermopile has an output
35 signal without offset drift, because there cannot be any output signal without input power. Second, the thermopile does not suffer from interference from any physical or chemical signals except light (which can easily be shielded) because the Seebeck effect and the photoelectric effect are the only two self-generating effects in silicon. Third, the thermopile
40 does not need any biasing. The read-out is very simple and only a voltmeter is required. Finally there is no interference caused by power supplies. The

other advantage is that a process which is C-MOS compatible is used. The sensor is so compatible with the existing silicon technology and may be integrated with the control circuit on the same substrate.

5

Description

The device is an integrated gas flow sensor composed of integrated thermocouples on a polycrystalline silicon membrane, suspended on a cavity on bulk crystalline silicon, used as substrate. The insulating layer between the membrane and the thermocouples is silicon dioxide or silicon nitride. A heated resistor is also integrated on the membrane [1]. In fig. 1 we can see : the silicon substrate (2), the polysilicon / SiO₂ membrane and the isolation (3), the polysilicon part of thermopiles (4), the aluminum part of thermopiles (5) and the cavity after porous silicon removal (6). The cavity under the membrane is formed by using bulk silicon micromachining. To this end, a porous silicon layer is formed locally on silicon by electrochemical dissolution of bulk crystalline silicon and it is then chemically removed by C-MOS compatible chemicals (HF:H₂O₂) in order to form the cavity. Before porous silicon removal, a bilayer consisting of the thermal isolation layer and polycrystalline silicon is deposited on top of the whole silicon area and it is etched selectively in order to define the membrane area. The cavity under the membrane may be as deep as several tens of μms [2]. Fig. 2 shows a top view (A) and a cross section (B) of the membrane, where we can see the monocrystalline silicon (1) and the membrane (2). The thermal isolation may also be obtained by a porous silicon oxide layer, so an alternative to the above process is to keep porous silicon in place and oxidize it.

The integrated thermocouples on the membrane are put in series and their number determines the sensitivity of the device. These thermocouples are in thin film form (parallel strips of Al/n-type polysilicon or p-type/n-type polysilicon) and they are connected together in series so as a total voltage difference is measured at the two ends of the thermocouple series. The measured voltage difference is due to a temperature difference, developed at the two ends of each thermocouple, due to Seebeck effect, when there is a temperature difference caused by the gas flow.

The whole process is C-MOS compatible and the main steps are described in fig.3 where we can see : the definition of porous silicon area (A), the definition of membrane area and lateral isolation (B), the first step in thermopile fabrication (C) and finally the second step of thermopile

3.

fabrication and porous etching. The main parts of the device are : porous silicon (1), silicon substrate (2), polysilicon / SiO_2 membrane and isolation (3), polysilicon strips - thermopiles (4), aluminum strips - thermopiles and pads (5) and cavity after porous silicon removal (6).

5

Claims

We claim :

1. An integrated gas flow sensor device characterized by :
 - 5 a sensing element composed of a series of integrated thermocouples(5,8) and a heated resistor(6) both integrated on a suspended membrane(3) composed of a bilayer of polysilicon/SiO₂ or polysilicon/silicon nitride. The membrane is suspended on a deep tunnel(10), formed into a monocrystalline silicon substrate(2). The deep tunnel(10) under the membrane(3) serves to thermally isolate the sensor from the silicon substrate(2). It is formed by
 - 10 bulk silicon micromachining, using a porous silicon layer(1) as sacrificial layer. The thermocouples are parallel strips in contact on one end, made of p-type polycrystalline silicon(5) / aluminum(5) or n-type / p-type polycrystalline silicon. The resistor(6) is also a strip made of polycrystalline
 - 15 silicon.
2. The fabrication process of a gas flow sensor as described in claim 1, characterized by C-MOS compatibility. All the processes and chemicals used are C-MOS compatible. A porous silicon layer(1) is formed on a pre-defined area by electrochemical dissolution of bulk crystalline silicon(2). A
- 20 bilayer of silicon dioxide and polycrystalline silicon(3) is then deposited on top by Low Pressure Chemical Vapour Deposition and etched by Reactive Ion Etching, in order to define the membrane area(3) and the pads(4). The thermopiles(5,8), the heater resistor(6), the stabilizer resistor(7) and the contact pads(9) are formed on the membrane(3) and on the pads(4) by first
- 25 depositing polysilicon which is doped with p-type dopants and etched selectively by Reactive Ion Etching and then by depositing aluminum, which is etched chemically. At the end of the process, the porous silicon layer(1) is removed by C-MOS compatible chemicals (HF:H₂O₂) and a deep tunnel(10) is thus formed under the membrane(3), which thermally isolates
- 30 the sensor from the bulk silicon substrate(2).
3. An alternative process to the fabrication process of claim 2, in which the thermal isolation between the membrane(3) and the bulk silicon(2) substrate is assured by the porous silicon layer which is thermally oxidized in order to achieve better thermal isolation properties. The thermal
- 35 conductivity of oxidized porous silicon is between two and three orders of magnitude lower than the thermal conductivity of monocrystalline silicon. So it provides thermal isolation close to that obtained by air which has a thermal conductivity four orders of magnitude below that of silicon.
4. Suspended membrane(3) fabrication process which is based on bulk
- 40 silicon micromachining and it is characterized by C-MOS compatibility as it is described in claim 2. The deep cavity(10) under the membrane may be as

deep as several tens of μms and it is fabricated by using porous silicon(1) as a sacrificial layer. A porous silicon layer(1), of a thickness of several micrometers to several tens of micrometers is fabricated locally on a predefined area by electrochemical dissolution of bulk crystalline silicon(2) through a mask made of a bilayer of SiO_2 and polycrystalline silicon. The membrane material(3) is then deposited on top of the whole wafer by Low Pressure Chemical Vapour Deposition and it is etched by Reactive Ion Etching in order to define the membrane area(3). The porous silicon(1) is then chemically removed by a solution of $\text{HF}:\text{H}_2\text{O}_2$ which is C-MOS compatible. A polysilicon bridge(3) is so formed with a deep tunnel(10) underneath. The bottom surface and sidewalls of the tunnel are very smooth.





Fig. 1/3

BEST AVAILABLE COPY




Fig. 2/3

BEST AVAILABLE COPY




Fig. 3/3

BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GR 97/00040

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G01F1/684 G01F1/688

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G01F G01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 195 20 777 C (INST PHYSIKALISCHE HOCHTECHNOL) 29 August 1996 see the whole document ---	1-4
A	DE 43 03 423 A (FRAUNHOFER GES FORSCHUNG) 11 August 1994 see column 2, line 44 - column 3, line 10; figures ---	1-4
A	DE 44 18 207 C (SIEMENS AG) 22 June 1995 see page 3, line 15 - line 60; figures ---	1-4
A	GB 2 251 312 A (BOSCH GMBH ROBERT) 1 July 1992 see the whole document ---	1-4
-/--		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

27 March 1998

Date of mailing of the international search report

03/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pflugfelder, G

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GR 97/00040

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 242 863 A (XIANG-ZHENG TU ET AL) 7 September 1993 see column 7, line 12 - line 61; figure 3 ---	1-4
A	US 5 231 878 A (ZANINI-FISHER MARGHERITA ET AL) 3 August 1993 cited in the application see the whole document ---	3
A	US 4 680 963 A (TABATA OSAMU ET AL) 21 July 1987 see the whole document -----	3

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GR 97/00040

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 19520777 C	29-08-96	NONE	
DE 4303423 A	11-08-94	NONE	
DE 4418207 C	22-06-95	EP 0684462 A JP 7326809 A US 5596219 A	29-11-95 12-12-95 21-01-97
GB 2251312 A	01-07-92	DE 4041578 A JP 4269628 A	02-07-92 25-09-92
US 5242863 A	07-09-93	CN 1055195 A	09-10-91
US 5231878 A	03-08-93	NONE	
US 4680963 A	21-07-87	JP 1787473 C JP 4076412 B JP 61170618 A	10-09-93 03-12-92 01-08-86

THIS PAGE BLANK (USPTO)